

Flushing Compound - Technical Data Sheet

Product Description

Supercoat™ Flushing Compound is a synthetic latex reinforced silica paste designed for use on cement render and masonry substrates. Primarily for the repair of stress cracking in masonry.

Specifications

MSDS	101 - Version 1.0
Appearance	White to Mid Cream
Vehicle Type	Adhesion Promoted Styrene Acrylic
Solvent	Water
Finish	Flat
Touch dry time	4 hours/2000 micron coat at 20°C
Dry film thickness	N/A
Solids Content	75%
Specific Gravity	1.24 - 1.34
Usual number of coats	1
Toxicity	No added Chromites or Lead
Thinning & cleaning	Water
Coverage	N/A
Pail type & size	Plastic 20L

Please Note

Do not apply at temperatures below 10°C or if it is likely to drop below 10°C during drying/curing time. Do not apply at temperatures over 30°C or if it is likely to go over 30°C during drying/curing time. Softens at temperatures over 70°C.

Manufacturer

Ironbark Technology Ltd
PO Box 2398, Dunedin, New Zealand.
Phone (03) 456 4222
info@ironbark.technology

The information contained herein is correct to the best of our knowledge. Due to product improvement and supply, these specifications may be subject to minor changes.