

Hoppertex - Technical Data Sheet

Product Description

Supercoat™ Hoppertex is a thick, high solids acrylic texture coat which can be used on commercial/industrial/residential buildings, fences or sound barriers. Supercoat™ Hoppertex is usually applied by conventional hopper gun to the wall to create a range of textured finishes.

Specifications

MSDS	020 - Version 1.0
Appearance	White to Mid Cream
Vehicle Type	Adhesion Promoted Styrene Acrylic
Solvent	Water
Finish	Flat
Touch dry time	2 hours at 20°C
Time to 2nd coat	24 hours at 20°C
Dry film thickness	1000 - 1750 microns
Solids Content	75%
Specific Gravity	1.24 - 1.34
Usual number of coats	1 or 2
Toxicity	No added Chromites or Lead
Thinning & cleaning	Water
Coverage	0.9m ² /L (depending on substrate profile and applicator)
Pail type & size	Plastic 8L & 15L

Please Note

Do not apply at temperatures below 10°C or if it is likely to drop below 10°C during drying/curing time. Do not apply at temperatures over 30°C or if it is likely to go over 30°C during drying/curing time. Softens at temperatures over 70°C.

Manufacturer

Ironbark Technology Ltd
PO Box 2398, Dunedin, New Zealand.
Phone (03) 456 4222
info@ironbark.technology